


**AFD:** 22.9  $\mu$   
**SD:** 5.9  $\mu$   
**CV:** 25.9 %  
**CF:** 88.9 %  
**Curve:** 29.8 Dg/mm  
**Min:** 22.2  $\mu$   
**Max:** 24.3  $\mu$   
**Staple:** 95.0 mm

% of Fibers

*Alpaca Fiber Testing USA*



**AFD:** 22.9  $\mu$   
**SD:** 5.9  $\mu$   
**CV:** 25.9 %  
**CF:** 88.9 %  
**Curve:** 29.8 Dg/mm  
**Min:** 22.2  $\mu$   
**Max:** 24.3  $\mu$   
**Staple:** 95.0 mm

